

SUPER GLOSS SYNTHETIC ENAMEL

DIRECTIONS FOR USE

For best result ensure surface is free from dust, dirt, grease, rust moisture and loose particles etc.

The contents of this tin are supplied at brushing consistency.

However, it can also be used for spraying or dipping.

The paint should be thinned with our recommended thinner to a consistency of 40 to 50 seconds on Ford cup No. 4 for spraying. The air pressure should be kept at around 50 lbs for best result in spray painting.

This paint dries very fast and a second coat may be given after six hours in summer and twelve hours in winter.



SUPER GLOSS SYNTHETIC ENAMEL

Decorative Paints | Industrial Paints | Powder Paints | Thinners

Works : 32 KM, Village Bija, Tehsil Khanna,
Ludhiana - 141412 (Pb.) INDIA.

Tel. No. +91-1628-289908-09 Fax No. +91-1628-289910

Email: info@eurodec.in URL : www.eurodec.in



Quality, start to finish

eurodec paints

SUPER GLOSS SYNTHETIC ENAMEL



FOR PROTECTION AND DECORATION...